

FIREBOARD

Material: Saudi Rockwool Fire Board

No #: SRWP

The product is made from molten basalt rocks spun to fine fibers and bonded with thermosetting Binder to form rigid Rockwool slabs.

The Material has good thermal, fire resistant, and acoustical properties it complies with the requirements of ASTM C612 with the following specifications:

DESCRIPTION

THICKNESS (MM)	DENSITY (KG/M ³)	FACING	ASTM CLASSIFICATION
50 -150	64 -200	None or Aluminum facing FSK / O class	Type IVA
THERMAL CONDUCTIVITY (AT 24° C) W/M.K	0.036- 0.034		EN 12667:2001 ASTM C177
MAX. USE TEMPERATURE	750 (°C)		ASTM C411
RIGIDITY	Rigid		ASTM C1101
COLOR	Yellowish		Visual
COMPRESSIVE RESISTANCE AT 10 % DEFORMATION (KPA)	4 - 60		ASTMC165
SHOT CONTENT	<25 % (weight %)		ASTM C612
CORROSIVENESS	Noncorrosive		ASTM C871 ASTM C795
WATER VAPOR SORPTION	<1 (Weight %)		ASTM C1104
PH	7-9		BS 2972 SEC 22
FLAME SPREAD INDEX	0		ASTM E84
SMOKE DEVELOPED	0		ASTM E84
FUNGI RESISTANCE	Does not encourage Fungi Growth		ASTM C665
EURO CLASS FIRE CLASSIFICATION	A1		EN ISO 13501-1
NOISE REDUCTION COEFFICIENT (NRC)	1		ASTM C423

Saudi Rockwool Factory

شركة المصنع السعودي لصناعة الصوف الصخري

T +966 11 265 0034 F +966 11 2650089

U 7001 454 920 E info@saudirockwool.com

P.O. Box 145 ص.ب. Riyadh 11383 الرياض
 المملكة العربية السعودية Kingdom of Saudi Arabia